











| |  | | |  | |  | |  | |  |  |  |
|-------------|---|-------|------|---|------|---|-------|--|--------|---|---|---|
| | DN | inch | size | mm | mm | bar | psi | bar | psi | mm | kg/m | |
| 616 911 006 | 06 | 1/4" | -04 | 9,9 | 12,0 | 210 | 3.045 | 840 | 12.180 | 45 | 0,17 | UF + 671 116 006 |
| 616 911 008 | 08 | 5/16" | -05 | 11,7 | 13,8 | 210 | 3.045 | 840 | 12.180 | 50 | 0,22 | UF + 671 116 008 |
| 616 911 010 | 10 | 3/8" | -06 | 13,2 | 15,8 | 210 | 3.045 | 840 | 12.180 | 60 | 0,27 | UF + 671 116 010 |
| 616 911 012 | 12 | 1/2" | -08 | 17,1 | 19,3 | 210 | 3.045 | 840 | 12.180 | 85 | 0,39 | UF + 671 116 012 |

Beispielhafte Layline:

 Exovation 1SE DN06 - 1/4" - WP 210 BAR (3.045 PSI)



Seele:

Spez. synthetisches Gummi

Druckträger:

1 hochzugfestes Stahldrahtgeflecht

Decke:

Spez. synthetisches Gummi

Anwendung:

Hochdruckschlauch zur Verwendung mit Mineralöl und biologischen Ölen

Sicherheitsfaktor:

1 : 4

Temperaturbereich:

- 40° C / + 100° C || kurzzeitig: + 120° C

Ozonbeständigkeit:

Nach EN 27326, 400 h

Abriebbeständigkeit:

Nach EN ISO 6945, 0,20 g

Tube:

Synthetic rubber

Reinforcement:

1 high tensile steel braid

Cover:

Synthetic rubber

Application:

High pressure hose for mineral and vegetable lubricants

Safety factor:

1 : 4

Temperature range:

- 40° F / + 212° F || short-term: + 248° F

Ozone resistance:

Acc. to EN 27326, 400 h

Abrasion resistance:

Acc. to EN ISO 6945, 0,20 g