














	DN		inch	size	mm	mm	bar	psi	bar	psi	mm	kg/m	
													
616 914 006	06	1/4"	-04	10,0	11,8	290	4.205	1.160	16.820	40	0,17	UF + 671 120 006	
616 914 008	08	5/16"	-05	11,6	13,6	250	3.625	1.000	14.500	55	0,23	UF + 671 120 008	
616 914 010	10	3/8"	-06	13,7	16,5	230	3.335	920	13.340	65	0,29	UF + 671 120 010	
616 914 012	12	1/2"	-08	16,9	19,0	200	2.900	800	11.600	80	0,34	UF + 671 120 012	
616 914 016	16	5/8"	-10	20,5	22,3	150	2.175	600	8.700	105	0,43	UF + 671 111 016	
616 914 019	19	3/4"	-12	24,0	26,2	150	2.175	600	8.700	120	0,53	UF + 671 111 019	
616 914 025	25	1"	-16	31,3	34,0	110	1.595	440	6.380	160	0,78	UF + 671 111 025	

Beispielhafte Layline:

 Exovation 1TP DN06 - 1/4" EN 857 - WP 290 BAR (4.205 PSI) 

Seele:

Spez. synthetisches Gummi

Druckträger:

1 hochzugfestes Stahldrahtgeflecht

Decke:

Spez. synthetisches Gummi

Anwendung:

Hochdruckschlauch zur Verwendung mit Mineralöl und biologischen Ölen

Sicherheitsfaktor:

1 : 4

Temperaturbereich:

- 40° C / + 100° C || kurzzeitig: + 125° C

Ozonbeständigkeit:

Nach EN 27326, 150 h

Abriebbeständigkeit:

Nach EN ISO 6945, 0,50 g

Tube:

Synthetic rubber

Reinforcement:

1 high tensile steel braid

Cover:

Synthetic rubber

Application:

High pressure hose for mineral and vegetable lubricants

Safety factor:

1 : 4

Temperature range:

- 40° F / + 212° F || short-term: + 257° F

Ozone resistance:

Acc. to EN 27326, 150 h

Abrasion resistance:

Acc. to EN ISO 6945, 0,50 g