












	DN	inch	size	mm	mm	bar	psi	bar	psi	mm	kg/m	
												
616 925 006	06	1/4"	-04	11,4	13,4	450	6.525	1.800	26.100	45	0,27	UF + 671 111 006
616 925 008	08	5/16"	-05	12,9	15,0	420	6.090	1.725	25.010	60	0,33	UF + 671 111 008
616 925 010	10	3/8"	-06	15,1	17,1	385	5.580	1.650	23.930	70	0,44	UF + 671 111 010
616 925 012	12	1/2"	-08	18,3	20,3	345	5.000	1.400	20.300	90	0,57	UF + 671 111 012
616 925 016	16	5/8"	-10	21,4	23,7	290	4.205	1.200	17.400	130	0,66	UF + 671 111 016
616 925 019	19	3/4"	-12	25,4	27,7	280	4.060	1.200	17.400	160	0,84	UF + 671 111 019
616 925 025	25	1"	-16	33,3	35,6	200	2.900	900	13.050	210	1,22	UF + 671 111 025
616 925 031	31	1 1/4"	-20	40,5	43,5	175	2.535	700	10.150	300	1,57	UF + 671 111 031

Beispielhafte Layline:

 Exovation 2TP-G DN06 - 1/4" EN 857 - WP 450 BAR (6.525 PSI)



Seele:

Spez. synthetisches Gummi

Druckträger:

2 hochzugfeste Stahldrahtgeflechte

Decke:

Spez. synthetisches Gummi

Anwendung:

Hochdruckschlauch zur Verwendung mit Mineralöl und biologischen Ölen

Sicherheitsfaktor:

1 : 4

Temperaturbereich:

- 40° C / + 100° C || kurzzeitig: + 120° C

Ozonbeständigkeit:

Nach EN 27326, 400 h

Abriebbeständigkeit:

Nach EN ISO 6945, 0,20 g

Tube:

Synthetic rubber

Reinforcement:

2 high tensile steel braids

Cover:

Synthetic rubber

Application:

High pressure hose for mineral and vegetable lubricants

Safety factor:

1 : 4

Temperature range:

- 40° F / + 212° F || short-term: + 248° F

Ozone resistance:

Acc. to EN 27326, 400 h

Abrasion resistance:

Acc. to EN ISO 6945, 0,20 g