














	DN	inch	size	mm	mm	bar	psi	bar	psi	mm	kg/m	
												
616 924 006	06	1/4"	-04	11,1	13,1	450	6.525	1.950	28.280	45	0,29	UF + 671 111 006
616 924 008	08	5/16"	-05	12,9	15,0	420	6.090	1.725	25.010	60	0,33	UF + 671 111 008
616 924 010	10	3/8"	-06	15,1	17,1	385	5.580	1.650	23.930	70	0,44	UF + 671 111 010
616 924 012	12	1/2"	-08	18,3	20,3	345	5.000	1.400	20.305	90	0,57	UF + 671 111 012
616 924 016	16	5/8"	-10	21,4	23,7	290	4.205	1.200	17.400	130	0,66	UF + 671 111 016
616 924 019	19	3/4"	-12	25,4	27,7	280	4.060	1.200	17.400	160	0,84	UF + 671 111 019
616 924 025	25	1"	-16	33,3	35,6	200	2.900	900	13.050	210	1,22	UF + 671 111 025

### Beispielhafte Layline:

 Exovation 2TP DN06 - 1/4" EN 857 - WP 450 BAR (6.525 PSI) 

#### Seele:

Spez. synthetisches Gummi

#### Druckträger:

2 hochzugfeste Stahldrahtgeflechte

#### Decke:

Spez. synthetisches Gummi

#### Anwendung:

Hochdruckschlauch für Landwirtschafts- und Baumaschinen zur Verwendung mit Mineralöl und biologischen Ölen

#### Sicherheitsfaktor:

1 : 4

#### Temperaturbereich:

- 40° C / + 100° C || kurzzeitig: + 125° C

#### Ozonbeständigkeit:

Nach EN 27326, 150 h

#### Abriebbeständigkeit:

Nach EN ISO 6945, 0,50 g

#### Tube:

Synthetic rubber

#### Reinforcement:

2 high tensile steel braids

#### Cover:

Synthetic rubber

#### Application:

High pressure hose for mineral and vegetable lubricants. Suitable for agricultural and construction machinery

#### Safety factor:

1 : 4

#### Temperature range:

- 40° F / + 212° F || short-term: + 257° F

#### Ozone resistance:

Acc. to EN 27326, 150 h

#### Abrasion resistance:

Acc. to EN ISO 6945, 0,50 g